

增强增韧 PA6 (RF-1331GF25)

Glass fiber reinforced PA6 (RF-1331GF25)

一般信息

General Information

特征 Features	● 25%玻纤增强 ● 低吸水 ● 耐热性	25Percents Glass Fiber Reinforced Low Water Absorption Heat Stabilized
应用 Uses	● 汽车 ● 建筑 ● 体育用品 ● 家用电器	Automotive Construction Industry. Sporting Goods Domestic Appliances
形态 Forms	● 粒子 ● Pellets	
加工方法 Processing Method	● 注塑 ● Injection Molding	
RoHS	● RoHS 合规	Meet the RoHS specification

产品性能

Typical Properties

	测试项目 Test Items	测试标准 Test standard	测试条件 Test Condition	典型值 Typical Value
物理性能 Physical	密度 Specific Gravity	ASTM D792	23°C	1.32g/cm3
	成型收缩率 Mold Shrinkage	ASTM D955	23°C	0.4-0.6%
力学性能 Mechanical	拉伸强度 Tensile Strength	ASTM D638	5mm/min	100MPa
	断裂伸长率 Tensile Elongation	ASTM D638	5mm/min	10%
	弯曲强度 Flexural Strength	ASTM D790	2mm/min	160MPa
	弯曲模量 Flexural Modulus	ASTM D790	2mm/min	5600MPa
	悬臂梁缺口冲击强度 Izod Notched Impact Strength	ASTM D256	23°C	105 J/m
	悬臂梁无缺口冲击强度 Izod Impact Strength	ASTM D256	23°C	850 J/m
	热变形温度 Heat Deflection Temperature	ASTM D648	1.82MPa	185°C
热性能 Thermal				
燃烧性能 Flammability	阻燃性能 Halogen-free Flame Retardant	UL-94	23°C	HB

加工信息**Processing Guidelines**

干燥条件 Drying	80°C-100°C, 4-6h
后段温度 Rear Temperature	220°C-240°C
中段温度 Middle Temperature	220°C-240°C
前段温度 Front Temperature	230°C-250°C
喷嘴温度 Nozzle Temperature	230°C-250°C
熔体温度 Melt Temperature	220°C-240°C
模温 Mold Temperature	80°C-100°C

备注:**Note:**

1. 所有数据为实验室典型值，仅供参考，不作为产品标准。

All data are typical values from laboratory. The data are used for reference only, not as production standard.

2. 生产时避免材料和其他材料、灰尘及杂物接触。

Avoid contact with other materials, dust and debris in the injection processing.

3. 注塑时避免材料长时间停留在螺杆中。

Avoid long time stay in the barrel in the injection processing.